

●/PR 7S

SPECIFICATION

PROCESS FOR PRODUCING LEAD-ACID BATTERY, AND  
JIG FOR PRODUCING LEAD-ACID BATTERY

TECHNICAL FIELD:

A present invention relates to a process for producing a lead-acid battery and more particularly, a process for producing a lead-acid battery related to welding of terminal portions of the battery, and a jig for producing the same.

BACKGROUND ART:

It is a conventional practice either to produce a lead-acid battery of a so-called bushing terminal type in which a lead bushing also serves as a terminal, by inserting an upper portion of a pole protruding upwards from a cell chamber within a battery container of an assembled lead-acid battery through an insertion hole in a lead bushing cast in a lid made of a synthetic resin by a cast molding process, and welding the pole inserted and the lead bushing around an outer periphery of the pole to each other, or to produce a lead-acid battery of a type having a terminal member led out sideways by mounting a separately fabricated terminal on an outer peripheral surface of a lead bushing, and welding the bushing and the terminal to each other using a burner.

In this case, at the time of welding using the burner, as mentioned above, in order to previously prevent that the lid would be deformed due to a welding heat, whereby an air-tightness failure would occur between the lid and the lead bushing

09/857187:062001

integrally cast in the lid, it has preferably practiced in general to carry out the burner welding in such a state that an annular mold of a jacket type for passing cooling water therethrough is disposed in contact with around the peripheral surface of the lead bushing or the peripheral surface of the terminal mounted on the bushing.

More particularly, in the case of producing the lead-acid battery of a bushing terminal type as described above, it has been conventional to weld terminal portions to be welded of the lead-acid battery, i.e., mutually abutted or adjacent peripheral portions of the lead bushing integrally cast in a lid made of a synthetic resin by an insertion molding and a pole of a battery body inserted through a cylindrical hole in the lead bushing to each other by a burner flame.

In the case of welding of the pole and the lead bushing using the burner, however, if the height from the surface of the lid to an upper end surface of the lead bushing is not more than 8 ~ 10 mm, in other words, is less than 8 ~ 10 mm, it is not avoidable that the lid is deformed due to the heat generated during the burner-welding, even if the above-mentioned cooling means is used, an air-tightness failure is occurred between the lid and the lead bushing formed in the lid. Therefore, it is required that the upper end of the lead bushing protrudes more than 8 ~ 10 mm from the surface of the lid, and hence, such a corresponding height-wise space enough to accommodate the lead bushing terminal is required above the upper surface of the lid. On the other hand, it is desirable to produce a lead-acid battery

09857187-052001

Therefore, it is desired to remove such inconveniences and develop a process capable of producing a lead-acid battery, wherein welding of the required portions can be achieved smoothly without any manufacture loss.

Accordingly, it is desired to remove such inconveniences and develop a process for producing a lead-acid battery by such a process for welding of the terminal portions that is capable of welding the terminal portions to each other stably and

Accordingly, it is desired to remove such inconveniences and develop a process for producing a lead-acid battery by such a process for welding of the terminal portions that is capable of welding the terminal portions to each other stably and

satisfactorily without any manufacture loss.

#### DISCLOSURE OF THE INVENTION:

It is an object of the present invention to provide a process for producing a lead-acid battery which has removed the problems associated with the prior arts, and the present invention is characterized in that a lead bushing integrally cast in a lid of an assembled lead-acid battery and a pole inserted through the lead bushing are welded together by a laser welding.

Further, a process for producing a lead-acid battery according to the present invention, is characterized in that welding of a lead bushing integrally cast in a lid of an assembled lead-acid battery and a pole inserted through the lead bushing and welding of the lead bushing and a tab terminal member fitly mounted on in the lead bushing are carried by a laser welding.

Further, in the process for producing the lead-acid battery according to the present invention, it is characterized in that at the time of the laser welding a laser beam of a low output is applied and thereafter a laser beam of a high output is applied.

Further, in the process for producing the lead-acid battery according to the present invention, it is characterized in that the laser welding is of a pulsed type.

Further, in the process for producing the lead-acid battery according to the present invention, it is characterized in that the lap density of beads in the laser welding of the pulsed type is in a range of 6 ~ 12 points per mm.

Further, it is an object of the present invention to provide

005718-05001  
10050-2375000

00857187 062001

a process for the laser welding of the terminal portions of the lead acid battery for preventing a laser beam from intercepting by fumes generated at the time of application thereof in the laser welding in the process for producing the above-mentioned lead-acid battery, to make it possible to carry out the welding at a high efficiency and stably and sufficiently, and it is characterized in that when the laser-welding is carried out by applying the laser to terminal portions to be welded of the lead-acid battery, there is used such a process for laser-welding of the terminal portions that the terminal portions are surrounded by a lower cylindrical end portion of a cylindrical shield, and, in this state, fumes generated at the time of the laser-welding are sucked to be exhausted to the outside of the cylindrical shield through an exhaust port in the cylindrical shield.

Further, it is an object of the present invention to provide a process for the laser welding of the terminal portions which is capable of carrying out the welding by application of the laser beam accurately and at a good efficiency when the above-mentioned process for laser welding is used in the above-mentioned process for producing the lead-acid battery, and it is characterized in that a discharge opening is provided in the cylindrical shield, and oxygen or air is supplied through the discharge opening to the portions to be welded.

Further, it is an object of the present invention to provide a process for laser welding for carrying out the laser welding more accurately and at a better efficiency when the

Further, the present invention, which is capable of carrying out the laser welding at a better efficiency while removing the fumes at a good efficiency by the laser welding when the above-mentioned laser welding is used in the above-mentioned process for producing the lead-acid battery, and it is characterized in that the plural communication bores made at regular intervals in the shroud ring are formed into those which are open in a circumferentially tangent direction of the ring, whereby an eddy flow is occurred to the fumes generated inside the shroud ring and is sucked to be exhausted.

Further, it is an object of the present invention to provide a laser welding jig which is suitable for carrying out the above-mentioned process for producing the lead-acid battery, and it is characterized in that an opening of the upper surface of a cylindrical body made of a metal having a good heat

conductivity is closed by a light-transmission plate and a lower cylindrical portion thereof is adapted to be fitted on the outer peripheral surface of the terminal portions of a lead-acid battery, so that a cylindrical shield is formed, and the cylindrical shield is provided with the plural discharge openings for a shield fluid disposed circumferentially at the lower portion thereof, and a shroud ring provided with the plural communication openings disposed at regular intervals circumferentially at a position which is above the discharge openings is so installed in the cylindrical shield as to leave an annular space between the shroud ring and the inner surface of a peripheral wall of the cylindrical shield, and the cylindrical shield is provided with an exhaust port which communicates with the annular space.

The disclosure of other characteristics of a process for producing a lead-acid battery and a welding jig used for the same according to the invention will be made clear in detail hereinafter.

#### BRIEF DESCRIPTION OF THE DRAWINGS:

Fig.1 is a partially cutaway side view of one example of an embodiment of a process for producing a lead-acid battery according to the present invention.

Fig.2 is a top view of a terminal portion of the lead-acid battery shown in Fig.1.

Fig.3 is a diagram for explaining a lap density of welding beads.

Fig.4 is a partially cutaway side view of another embodiment of a process for producing a lead-acid battery according to the present invention.

Fig.5 is a top view of a terminal portion of the lead-acid battery shown in Fig.4.

Fig.6 is a side view of a laser-welding jig according to one embodiment of the present invention for use in the process for producing the lead-acid battery according to the present invention.

Fig.7 is a sectional view taken along a line VI-VI in Fig.6.

Fig.8 is a sectional view taken along a line VII-VII in Fig.7.

Fig.9 is a partially cutaway perspective view for explaining one example of a process for laser welding used in the present invention.

Fig.10 is a sectional view of a portion of Fig.9 showing one example of a laser-welded state of terminal portions of a lead-acid battery.

Fig.11 is a graph for explaining a most preferable embodiment of a laser-welding process for use in the process for producing the lead-acid battery according to the present invention.

Fig.12 is graph for explaining a depth of uniform weld over the entire circumference of the welded terminal portions in the most preferable embodiment.

Fig.13 is a centrally vertical sectional view of another embodiment of an apparatus used in a process for producing a

100250 2372500



lead-acid battery according to the present invention.

#### BEST MODE FOR CARRYING OUT THE INVENTION:

The present invention will now be described in detail for more clarification, with reference to the accompanying drawings.

Figs. 1 and 2 show one embodiment of the present invention suited for to a process for producing a lead-acid battery of a type having a lead bushing terminal. Fig. 1 is a partially cutaway side view of an assembled lead-acid battery A in such a state that a laser nozzle connected to a laser-generating device (not shown) is disposed above the upper surface of terminal portions of a pole to be welded of the assembled lead-acid battery A, and Fig. 2 is a top view of a lid thereof.

More specifically, the assembled lead-acid battery A comprises a mono-block type lead-acid battery, for example, comprising six cells. In the drawings, reference character a designates a molded battery container made of a synthetic resin such as polypropylene, and reference character b designates a molded lid for the battery container which is abutted against and air-tightly bonded to the upper surface of the container a, which has an upper flat surface and which is provided with a lead bushing 1 integrally cast therein by a casting process using a synthetic resin such as polypropylene as a raw material. The lead bushing 1 is preferable to be made using, preferably, lead alloys such as Pb-Ca-Sn, etc. as a material. According to the present invention, the lead bushing 1 is so cast that a projected height h from the upper surface of the lid b to the

F00390-2B725800

Cells contained in respective cell chambers c in the container a are connected in series, as usual, and the lead-acid battery is assembled in such a manner that an upper portion 2a of a positive pole 2 protruding upwards from a strap e connecting, for example, ears of the positive plates d, d, ... among positive and negative plates constituting the cell in the cell chamber c at one end of the container a is inserted through an insertion hole 3 of the lead bushing 1 located at a corner portion of one side of the container lid b, as shown in the drawings, and an upper portion of a negative pole protruding upwards from a strap connecting negative plates of the cell in the cell chamber at the other end of the container a is inserted through an insertion hole in a lead bushing likewise cast therein, though not shown. According to the present invention, the upper portion 2a of the positive pole 2 of the lead-acid battery thus assembled and the projection portion 1a of the lead bushing 1 around the outer peripheral surface thereof are welded together by a laser welding, and the upper portion of the negative pole and the projection of the lead bushing around an outer periphery thereof are welded together similarly by a laser welding. For convenience, only the laser welding of the pole 2 which is the positive pole and the lead bushing 1 on one side as shown in Fig.1 will be described below in detail. The description the laser welding on the negative pole side is omitted, because it is carried out in the

According to the present invention, a laser-welding nozzle 4 is placed at a desired height distance spaced apart from the upper end of the lead bushing 1 above the positive pole 2 and the lead bushing 1 around the outer periphery thereof, and a plate-shaped transparent shield glass 5 is placed below the welding nozzle 4. The shield glass 5 is disposed just below the nozzle 4 through a support leg 6 depending vertically therefrom, or is placed on the upper surface of a cylindrical mold 7 which is placed on the upper surface of the lid b, and also is fitly mounted on the outer peripheral surface of the projection 1a of the lead bushing 1 to support the lead bushing 1, as shown by phantom lines. The mold 7 shown in the drawings, in other words, a jig is a cylindrical mold made of copper having a good thermal conductivity which also serves acts to cool the lead bushing 1 heated during the welding, and the inner peripheral surface of the upper portion thereof is formed into a trumpet-shaped slant surface 7a spread upwards, so that the shield glass 5 is placed stably on the inner peripheral slant surface 7a. It is not necessary for mold 7 made of copper to provide an equipment of a jacket type through which cooling water is passed as conventional, and to carry out a cooling operation while passing water therethrough. The shield glass 5 is for protecting the laser nozzle 4 from deposition of sputtered lead produced when a laser beam 4b from the laser nozzle 5 is applied to the upper surfaces of the pole 2 and the lead bushing 1 as shown in Fig.1 for welding them to each other. The height

The nozzle 4 is connected to a predetermined laser-generating source not shown through an optical fiber 4b. A type of a laser is for example, a YAG laser by which the laser welding according to the present invention is carried out. A method of the laser welding may be either a continuous welding one or a pulsed welding one, but, in a case where the depth of weld (penetration) of lead or a lead alloy is required to be made deep, the pulsed welding method is preferable. The laser welding according to the present invention is carried out by applying a laser beam of an high output, for example, 6 ~ 8 Joules enough to weld the lead or lead alloy, to and along the mutually abutted or adjacent circular portions 8 of the outer peripheral surface of the pole 2 and the outer peripheral surface of the lead bushing 1 or their vicinities, and moving it at least one round while welding the portions 8 together, so that welding between the pole 2 and lead bushing 1 is welded together to form a laser-welded terminal portion. It is sufficient if the depth of weld or penetration of the laser-welded portion is at least about 2.5 mm. The present inventors have found that, according to this laser-welding, even if the height of the lead bushing 1 from the upper surface of the lid b is only 4 mm, a stable and good welding the pole 2 and the bushing 1 together can be achieved without occurrence in the thermal deformation of the lid b. Accordingly, in respect of the lead-acid battery thus produced according to the present invention, the lead bushing

terminal protruding from the upper surface of the lid b is as only low as 4 mm, so that there is brought about such an effect that the height space above the terminal can be lowered remarkably, as compared with 8 ~ 10 mm or more conventionally required.

In addition, the pole 2 and the bushing 1 are made of lead or a lead alloy, and it is general and preferable that both members are made using the same material.

In a case where the pole 2 and the bushing 1 are made of a lead alloy, any of various kinds of a lead alloy such as a Pb-Sb alloy, a Pb-Ca-Sn alloy, a Pb-An alloy, a Pb-Sb alloy and the like can be used and is suitably used for the laser welding, but it has been found that the surface of a Pb-Ca based alloy which is liable to be oxidized in particular is coated with a black oxide film by the air, so that it is increased in absorptivity of the laser beam and is suited for carrying out a relatively deep weld by the laser-welding.

When the laser welding according to the present invention is carried out, the following phenomenon has been found.

Namely, when a laser beam of a high output is applied from the beginning to the surface of the lead busing 1 and that of the pole 2, it has been observed that the lead or lead alloy on the surfaces thereof is sputtered vigorously and explosively to become so-called sputtered lead and adhere to the surface of the shield glass 5 positioned thereabove, and thereby the laser beam is intercepted. Therefore, the laser welding is carried out sufficiently at the start of the laser welding, but the laser welding power is reduced with the lapse of time and

F00220 2872500

thus, there is a fear that the mutually abutted annular portions 8 cannot be welded to each other sufficiently by the laser welding. As a result of various experiments, it has been proved that if in the first place, a laser beam 5b is applied at such a low output that produces no sputtering and is moved one round along the entire circumferential surfaces of the pole and the lead bushing, and thereafter it is applied at a high output, a satisfactory laser-welding is achieved at a high efficiency and with a high energy over the entire circumferential surfaces thereof.

A comparison test example will be described in detail below.

At the time of welding the whole circumferences of the mutually abutted annular portions 8 of the pole 2 and the lead bushing 1 to be welded by the pulsed laser-welding, respective welded portions obtained by such a laser-welding case (an example of the present invention) that a laser beam of a low output as low as  $0.8 \sim 1.5$  Joules /pulse was firstly applied to the fire entirely circumferential surfaces of mutually abutted portions 8 and the vicinities thereof to break the lead oxide film, and a laser beam of a high output as high as  $6 \sim 8$  Joules/pulse was then applied to the entire circumferences thereof, thereby achieving the laser welding, and by such a laser-welding case (a comparative example) that a laser beam of a high output as high as  $6 \sim 8$  Joules/pulse was carried out from the beginning, were cut, respectively, by a line connecting between a starting point of the welding 8a indicated by a mark X on the mutually

100290-29425550

abutted annular portions 8 in Fig.2 and a mid point 8b of the welding which is on the opposite side of the welding-starting point 8a and indicated by a mark  $\Delta$ , and a depth of weld (penetration) of each of the respective welded portions of the cut surfaces thereof was measured, and there were obtained the results shown in Table 1 below.

Table 1

	Depth (mm) of weld (penetration)	
	Starting point of the welding	Mid point of the welding
Example	2.4 ~ 2.6	2.4 ~ 2.6
Comparative Example	2.4 ~ 2.6	1.5 ~ 2.0

As is clear from Table 1 above, when the laser beam of the low output was first applied and the laser beam of the high output is then applied, according to the present invention, there was obtained a good weld in which the depths of welds at both of the starting point of the welding and the mid point of the welding were the same about 2.5 mm which is a satisfactory weld. In contrast therewith when the welding is carried out using the laser beam of the high output from the beginning, there is obtained a good weld in which the depth of weld at the start point of the welding is about 2.5 mm which is a satisfactory weld, but the depth of weld at the mid-point of the welding in the course of the welding was as shallow as 1.5 ~ 2.0 mm which is found to be insufficient in the depth of weld. This difference between the superiority and the inferiority is particularly remarkable in a case of using any of Pb-Ca based alloys that an oxide film is produced on the surface thereof.

T00000: 20250601

Further, it has been proved that when the pulsed laser welding was carried out by applying a laser beam of a high output to and along the mutually abutted portions 8, the number of the beads of the welding overlapped per 1 mm, i.e., a lap density of the beads, as shown in Fig.3, has various influences on the weld state, as described hereinafter.

Namely, 100 assembled lead-acid batteries as shown in Fig.1 were used as samples, and the welding was carried out in such a manner that a laser beam of a low output as low as 0.8 Joules/pulse was applied to the surfaces of the lead bushing 1 and the pole 2 of each of the 100 assembled lead-acid batteries, and thereafter a pulsed laser beam of a high output as high as 6 ~ 8 Joules/pulse was applied to the mutually abutted portions 8 by changing the lap density of the beads (having a diameter of 2 mm) variously. A depth of weld (penetration), a rate of generation of pinholes and a rate of generation of lack of air-tightness caused by the deformation of the lid were examined for each of the samples. Results are as shown in Table 2 below.

Table 2

Lap number of beads piled per mm (points)	Depth of weld (penetration) (mm)	Rate of generation of pinholes (%)	Rate of generation of lack of air-tightness (%)
0	0.8	48	0
3	1.4	20	0
6	2.5	0	0
9	3.0	0	0
12	3.3	0	0
15	3.9	0	27



On the other hand, in the case where the lap number of beads per mm was 6 points ~ 12 points, the depth of penetration was so deep as 2.5 ~ 3.3 mm, and also no pinhole passing through the penetration portion was generated to obtain stable and good laser-welds. In the case where the lap number of beads per mm was 15 points, it has been found that the depth of penetration became 3.9 mm, which was too deep, and the lid b was thermally deformed, and the air-tightness with the lead bushing cast in the lid b was broken to generate the lack of air-tightness.

Consequently, it has been found that in the case where the lap number of beads /mm within the length of 1 mm is in a range of 6 points ~ 12 points, stable and good laser welding can be carried out.

5-7-12

273566  
 273567  
 273568  
 273569  
 273570  
 273571  
 273572  
 273573  
 273574  
 273575  
 273576  
 273577  
 273578  
 273579  
 273580  
 273581  
 273582  
 273583  
 273584  
 273585  
 273586  
 273587  
 273588  
 273589  
 273590  
 273591  
 273592  
 273593  
 273594  
 273595  
 273596  
 273597  
 273598  
 273599  
 273600  
 273601  
 273602  
 273603  
 273604  
 273605  
 273606  
 273607  
 273608  
 273609  
 273610  
 273611  
 273612  
 273613  
 273614  
 273615  
 273616  
 273617  
 273618  
 273619  
 273620  
 273621  
 273622  
 273623  
 273624  
 273625  
 273626  
 273627  
 273628  
 273629  
 273630  
 273631  
 273632  
 273633  
 273634  
 273635  
 273636  
 273637  
 273638  
 273639  
 273640  
 273641  
 273642  
 273643  
 273644  
 273645  
 273646  
 273647  
 273648  
 273649  
 273650  
 273651  
 273652  
 273653  
 273654  
 273655  
 273656  
 273657  
 273658  
 273659  
 273660  
 273661  
 273662  
 273663  
 273664  
 273665  
 273666  
 273667  
 273668  
 273669  
 273670  
 273671  
 273672  
 273673  
 273674  
 273675  
 273676  
 273677  
 273678  
 273679  
 273680  
 273681  
 273682  
 273683  
 273684  
 273685  
 273686  
 273687  
 273688  
 273689  
 273690  
 273691  
 273692  
 273693  
 273694  
 273695  
 273696  
 273697  
 273698  
 273699  
 273700  
 273701  
 273702  
 273703  
 273704  
 273705  
 273706  
 273707  
 273708  
 273709  
 273710  
 273711  
 273712  
 273713  
 273714  
 273715  
 273716  
 273717  
 273718  
 273719  
 273720  
 273721  
 273722  
 273723  
 273724  
 273725  
 273726  
 273727  
 273728  
 273729  
 273730  
 273731  
 273732  
 273733  
 273734  
 273735  
 273736  
 273737  
 273738  
 273739  
 273740  
 273741  
 273742  
 273743  
 273744  
 273745  
 273746  
 273747  
 273748  
 273749  
 273750  
 273751  
 273752  
 273753  
 273754  
 273755  
 273756  
 273757  
 273758  
 273759  
 273760  
 273761  
 273762  
 273763  
 273764  
 273765  
 273766  
 273767  
 273768  
 273769  
 273770  
 273771  
 273772  
 273773  
 273774  
 273775  
 273776  
 273777  
 273778  
 273779  
 273780  
 273781  
 273782  
 273783  
 273784  
 273785  
 273786  
 273787  
 273788  
 273789  
 273790  
 273791  
 273792  
 273793  
 273794  
 273795  
 273796  
 273797  
 273798  
 273799  
 273800  
 273801  
 273802  
 273803  
 273804  
 273805  
 273806  
 273807  
 273808  
 273809  
 273810  
 273811  
 273812  
 273813  
 273814  
 273815  
 273816  
 273817  
 273818  
 273819  
 273820  
 273821  
 273822  
 273823  
 273824  
 273825  
 273826  
 273827  
 273828  
 273829  
 273830  
 273831  
 273832  
 273833  
 273834  
 273835  
 273836  
 273837  
 273838  
 273839  
 273840  
 273841  
 273842  
 273843  
 273844  
 273845  
 273846  
 273847  
 273848  
 273849  
 273850  
 273851  
 273852  
 273853  
 273854  
 273855  
 273856  
 273857  
 273858  
 273859  
 273860  
 273861  
 273862  
 273863  
 273864  
 273865  
 273866  
 273867  
 273868  
 273869  
 273870  
 273871  
 273872  
 273873  
 273874  
 273875  
 273876  
 273877  
 273878  
 273879  
 273880  
 273881  
 273882  
 273883  
 273884  
 273885  
 273886  
 273887  
 273888  
 273889  
 273890  
 273891  
 273892  
 273893  
 273894  
 273895  
 273896  
 273897  
 273898  
 273899  
 273900  
 273901  
 273902  
 273903  
 273904  
 273905  
 273906  
 273907  
 273908  
 273909  
 273910  
 273911  
 273912  
 273913  
 273914  
 273915  
 273916  
 273917  
 273918  
 273919  
 273920  
 273921  
 273922  
 273923  
 273924  
 273925  
 273926  
 273927  
 273928  
 273929  
 273930  
 273931  
 273932  
 273933  
 273934  
 273935  
 273936  
 273937

In this embodiment, a structure of the assembled lead-acid battery A' is such that there is formed a notched space 9' in lib b' at the corners of one end and the other end thereof, and a lead bushing 1 is cast in a lid portion b'1 formed at a lower level at bottom surface of the notched space 9. In this case, the height of a projection portion 1a of the lead bushing 1 from the upper surface of the lid b'1, i.e., the height h of the projection portion 1a to the upper end surface of the lead bushing 1 is set at 4 mm which is the same, as in the previous embodiment, and the upper portion 2a of a pole 2 protruding upwards from a negative strap e of a cell in a cell chamber c at one end of a battery container a' is inserted through an insertion hole 3 of the lead bushing 1. Further, a tab terminal member 10 comprising a prolong plate having the thickness of about 3 ~ 4 mm most preferably, a tab terminal member 10 comprising a prolong plate made of lead or a lead alloy, is fitly mounted on the outer peripheral surface of the columnar lead bushing 1 through a circular fitting hole 11 so made in one end thereof as to have a diameter fitly mountable on the outer surface of the lead bushing 1, and the other end of the tab terminal member 10 having a bolt-insertion hole 12 is positioned to protrude horizontally outwards from a side face of the lead-acid battery A'. It is preferable that a material for the tab terminal member 10 is the same lead alloy as that for the lead bushing 1.

Further preferably, a cylindrical mold 7' made of copper is fitly mounted on and in contact with the peripheral surface of the projection 1a of the lead bushing 1 and a semicircular peripheral surface of an outer peripheral edge of the fitted end portion 10a of the tab terminal member 10, and in addition is placed on the upper surface of the lid portion b'1 in contact with the upper surface and opposite sides of the tab terminal member 10, with a rectangular notch portion 7'b formed at the lower end of the mold 7' being across the same, so that the mold 7'b also serves to cool the lead bushing 1 at the time of the laser-welding.

For the laser welding, a laser nozzle having a condenser lens therein is disposed at a height position which is about 100 mm spaced upwards apart from the upper surface of the lead bushing 1, while the shield glass 5 is disposed below the laser nozzle 4, in the same manner as in the previous embodiment.

Figs. 4 and 5 show such a state that the mutually abutted annular portions 8 of the pole 2 and the lead bushing 1 around the outer periphery of the pole 2 have been already welded together to each other by the same laser welding as in the previous embodiment, so that a welded portion 8a has been well formed.

Further, according to the present invention, in order to weld the lead bushing 1 and the tab terminal member 10 therearound to each other, the laser welding of the both is carried out by applying a laser beam 5a from the laser nozzle 5 to mutually abutted annular portions 13 of the lead bushing 1 and the tab terminal member 10 through the glass shield 5. In this case,

00857187 052001

as for a method of laser-welding, either a continuous welding type one or a pulsed welding type one may be adapted and the laser beam thereof is applied or irradiated, in the same manner as explained in the previous embodiment. Preferably, by the pulsed welding, a laser beam of a low output as low as 0.8 ~ 1.5 Joules/pulse is first applied to the surface of the lead terminal member 10 to expose lead inside the lead terminal member 10 to the outer surface thereof, and then, a laser beam of a high output as high as 6 ~ 8 Joules/pulse and in a range of 6 points ~ 12 points of the lap number of beads/mm is applied, thereby the laser welding of the projection 1a of the lead bushing 1 and the lead tab terminal member 10 therearound to each other is carried out, so that production of a lead-acid battery is completed.

The heat generated from the start of the laser welding to the end thereof is remarkably small, as compared with that generated by a burner, so that there is occurred no thermal deformation of the lid. It is the same as in the previous embodiment that the cooling by the mold made of copper suffices, and that the conventional water-cooling is not required.

Furthermore, when the laser welding of the tab terminal member 10 is carried out, it is optional that after either a previous soldering is applied to the portions to be welded, or a ring-shaped solder is placed thereon, and thereafter the laser welding is carried out.

Thus, according to the present invention, when the welding of the lead bushing cast in the lid of the assembled lead-acid

0057137-032004

battery and the pole inserted through the lead bushing and further the welding of the lead bushing and the terminal member fitted on the lead bushing are carried out by the laser welding, even if the height of the lead bushing from the upper surface of the lid is remarkably lower than the case of the conventional art, a good welding can be achieved without exertion of an adverse affection onto the lid, and a stable and good lead-acid battery can be produced. Particularly, the lead-acid battery of the type having the terminal led out sideways can be produced smoothly, which is advantageous.

In this case, as mentioned above, if the laser beam of a low output of such a degree that produces no sputtering is first applied and is moved one round and thereafter a laser beam of a high output is applied and moved one round to and along the applied locus or trace of the laser beam of the low output, the laser welding of a predetermined depth can be achieved over the whole circumference without adhering sputtered leads to the shield glass. Particularly, when the pulsed type one as a laser welding method is carried out, the depth of weld can be more increased to provide a firm weld.

When the bushing 1 and the pole made of any of various kinds of lead alloys are welded to each other by applying the above-mentioned laser beam of the low output or/and the high output to the mutually abutted annular portions 8 or their vicinities and making it at least one round therealong, there is a fear that fumes generated during the welding are adhered to the shield glass 5 to intercept the passing of the laser beam

100290-28125850

therethrough and, as a result, the welding energy is lowered, and there can not be obtained a predetermined uniform or equal depth of penetration over the whole circumference, and in some cases, there can not be obtained a lead-acid battery provided with a terminal portion welded stably and satisfactorily.

An embodiment of the present invention removing such a fear will be described in detail with reference to Figs. 6 to 10.

In Figs. 6 to 10, reference character B designates one example of a laser-welding jig according to the present invention for use in carrying out the above-mentioned laser-welding process used in the process for producing a lead-acid battery according to the present invention. A cylindrical body 70a of a cylindrical shield 70 constituting a main body of the jig B is formed into a circular one made of a metallic material having a good thermal conductivity, for instance, a metal which is high in thermal conductivity such as copper and a copper alloy, and corresponds to the mold 7 also serving as the cooling action in the previous embodiment. The cylindrical shield 70 is so constructed that an opening in the upper surface of the cylindrical body 70a is closed by a light-transmission plate 5 permeable to a laser beam, in general, by a heat-resistant glass plate 5, and the lower end portion thereof is formed into a cylindrical lower end portion 70a1 having the inner diameter suitable being fitly mounted on the outer peripheral surface of a terminal portion of a lead-acid battery. Further, the plural number, preferably, three or more of discharge openings 14, 14, ... are disposed at regular intervals

T00290-237-062001

**THE**

50B  
A3

**0-876-934-1**

Further, at the time of using thereof a connecting tube 22 such as a pressure tube is connected at one end thereof in a band-manner to the tubular exhaust port 18 and at the other end thereof to an external vacuum pump, so that fumes generated within the jig B during the welding may be sucked and exhausted at a desired negative pressure.



Next, one example of a process for producing a lead-acid battery having a terminal welded by the above-mentioned laser-welding process according to the present invention by using the above-mentioned jig B according to the present invention will be described with reference to Figs. 9 and 10.

The lower cylindrical end portion 70a1 of the cylindrical shield 70 of the jig B according to the present invention is fitly mounted on the outer peripheral surface of a terminal portions T comprising an upper end portion 1a of a lead bushing 1 cast in a container lid b'' made of a synthetic resin in a lead-acid battery A'', and an upper end portion 2a of a positive or negative pole, e.g., of a positive pole 2 in the illustrated embodiment inserted through an insertion hole 3 of the lead bushing 2, and in other words, on an outer peripheral surface of the upper end 1a of the lead bushing 1, and therefore the inside of the cylindrical shield 70 is made airtight. On the other hand, the discharge openings 14, 14, 14 disposed in the lower portion of the cylindrical shield 70 are connected to an external common compression pump (not shown) through the connecting tubes

A laser nozzle 4 led out, for example, from a pulsed type laser generator (not shown) is so positioned above the jig B placed on the battery lid b'' surrounding the terminals T, as described above, so that a laser beam 4b may be directed as shown by an arrow, through an incident lens within the laser nozzle 4 toward a target of the portions to be welded, i.e., toward one point of mutually abutted circular portions 8 constituting the terminal portions T composed of a projection 1a' of a lead bushing 1' and an upper portion of either a negative or a positive pole, that 2a' of the positive pole 2' in the illustrated example, inserted through the insertion bore in the lead bushing 1'. At this time, the distance between the portions 8 to be welded and the laser nozzle 4 is set to be equal to a focal distance of the incident lens within the laser nozzle 4. In the case of application of the laser beam, the laser nozzle 4 is moved round at a radius equal to the radius of the circular portions 8 to be welded, thereby applying the laser beam at least one round to the entire circumference of the portions 8 to be welded, thus welding the portions 8 together. In this case, the application conditions of the laser beam are, for example, such that a quantity of application heat is in a range of 5 ~ 10 Joules/pulse and that the application intervals are in a range

[illegible]

On the other hand, a decompression device such as a vacuum pump, etc. is driven to perform an evacuation at a desired negative pressure through the tubular exhaust port 18, whereby fumes generated within the cylindrical shield 70 during welding of the portions to be welded is sucked and exhausted immediately from the cylindrical shield 70 to the outside, so that the fumes are prevented from adhering to the shield glass 5 and intercepting the passing of the laser beam therethrough. Accordingly, a good laser welding of a depth of penetration uniformly welded over the whole circumference of the portions 8 without any reduction in a predetermined laser output. The shielding fluid flowed

In this case, when the communication openings 15, 15, ... are made in the circumferentially tangent direction in the shroud ring 16 as mentioned above, an eddy flow is caused to occur in the flow of the exhaust gas, and the exhaust gas can be sucked to be exhausted smoothly and quickly as a flow in a given definite direction. Thus, the discharge amount of the shielding fluid to be flowed into the cylindrical shield 70 through the discharge opening 14 and the exhaust amount of the shielding fluid to be sucked and exhausted is adjusted as desired to any of various values and a desired preferable laser welding can be carried out. For this purpose, the discharge pressure and discharge flow rate of the shielding fluid by the compression pump and the exhaust pressure and exhaust rate of the exhaust fluid by the vacuum pump are adjusted to any of various values, and particularly, it is preferable to set in a range of 60 ~ 80 KPa, the discharge flow rate in a range of 15 ~ 20 liters/min, the discharge pressure in a range of 300 ~ 450 Pa and the exhaust flow rate in a range of 4 ~ 5 m<sup>3</sup>/min.

If the discharge pressure and flow rate of the shielding fluid are larger than the above-mentioned values, the fused lead

[illegible][illegible][illegible]

Furthermore, in the embodiment shown in Fig.9 above, the welding of the annular portions 8 to be welded was carried out for 100 pieces of the lead-acid battery provided with the terminal portions to be welded by applying a laser beam at a low output of 3.8 Joules/pulse while moving the first rotation (the first round) along the portions 8 to be welded to break the oxide film, and then applying a laser beam of a high output reduced stepwise at a plurality of stages, for example, of 11.5 Joules/pulse, 10.8 Joules/pulse, 10 Joules/pulse and 9.2 Joules/pulse while moving the second rotation (the second round), as shown in Fig.11. It has been found that the first round and the second round result in that the depth of weld is substantially uniformly within a range 4 ~ 6 mm over the whole circumference of the annular portions to be welded, as shown in Fig.12, and the resin of the lid b'' around the terminal portion T is not softened or molten at all, and accordingly, there can be obtained assuredly the lead-acid batteries with an air-tightness being well maintained without transuding of the electrolyte. Further, the number of the stages of the stepwise high outputs is not limited, but about 2 ~ 8 stages are preferable from the viewpoints of the quality, the producing equipment and the like.

Further, the example in which the discharge opening 14 is made in the cylindrical shield 70 and the oxygen or air is supplied therethrough has been shown as one example of the embodiment of the present invention. However, only if the fume is removed, it can be achieved only by suction through the exhaust port 18. In this case, a suitable gap is created so that

09857187-062001

compression in the cylindrical shield 70 may not be reduced. For example, it is arranged that gaps are created between the lower end portion of the cylindrical shield 70 and the surface of the lid or between the lower cylindrical end portion 70a1 and the outer peripheral surface of the terminal portions T, or that the provision of the annular packing 20 is omitted, so that the open air is flowed by the suction into the cylindrical shield 70 through a gap between the annular shield cap 19 and the glass plate 5. In this case, since the open air is flowed by the suction into the cylindrical shield 70 through these gaps, oxygen is supplied and the depth of weld can be deepened, which is preferable.

Thus, according to the present invention, since the laser welding of the terminal portions to be welded is carried out in such a manner that in such a state that the terminal portions of the lead-acid battery is surrounded by the lower cylindrical end portion of the cylindrical shield, the shield fluid is flowed thereinto through the discharge opening made in the cylindrical shield and is brought into contact with the terminal portions to be welded, and meanwhile, fumes generated during the laser welding is removed by suction through the exhaust port made in the cylindrical shield, and the reflection of the laser beam is inhibited by the shielding fluid and the laser welding can be carried out at a good efficiency, and also the intercepting of the laser beam by fumes for intercepting the laser beam can be prevented and the lowering of the sufficient laser output can be prevented and the welding efficiency is improved and also

00857187 062001

**POLYMER LETTERS**

[illegible][illegible][illegible]



As for the lead bushing 1 through which the pole 2 inserted and by which it is surrounded, an outer peripheral surface of the protrusion portion 1a thereof is formed with an annular notched step 1b. A laser-welding jig B' has such a construction that an annular shield cap 20' which surrounds and holds a light-transmission glass 5', and in which the plural number of, for instance, six of circular air-intake openings 23, 23, ... each having a diameter of about 5 mm are made at equal intervals circumferentially is secured to an upper surface of a cylindrical shield 70' made of a good thermal conductivity, and an exhaust tube 21' having an inside diameter of about 30 mm is provided on an upper cylindrical wall 70a3' of the cylindrical shield 70'. In use, the laser-welding jig B' is placed so that the lower cylindrical end 70a1' thereof may be fitly mounted on the outer peripheral surface of the protrusion 1a of the lead bushing 1 and also placed on a surface of the annular notched step 1b, as shown in Fig.13. In Fig.13, reference character 15' designates a communication opening disposed in the shroud ring 16'; reference character 17' designates an annular space; and reference character 22' designates a connecting tube connected to the exhaust tube 21'.

Thus, the laser welding is carried out in such a state that the lower cylindrical end 70a1' of the laser-welding jig B' is fitly mounted on the annular notched step 1b provided on the outer peripheral surface of a terminal T, in other words, on the outer peripheral surface of the protrusion 1a of the lead bushing 1 thereof, and, in the illustrated embodiment, a laser

100290 2872560

5  
A 763

nozzle 4 is so positioned so that a laser beam 4b converged by a condenser lens 4c may be focused to hit on the outer side portion about 0.15 mm from the boundary of the annular abutted portions 8 (with a gap of 0 ~ 0.5 mm left therebetween) between the outer peripheral surface of the pole 2 and the inner peripheral surface of the lead bushing 2, and in other words, the laser beam 4b may hit on the inner peripheral edge of the lead bushing 1. And laser nozzle 4 is moved round along the inner peripheral edge of the lead bushing so that the laser beam 4b thereof may be applied thereto and, meanwhile, the evacuation by suction is conducted through the exhaust tube 21' and the connecting tube 22'. The laser welding is carried out in the above-mentioned manner that the laser beam of such a low output that generates no sputtering, was made one round and thereafter the laser beam of a high output was made one round. Thus, the laser welding between the pole 2 and the lead bushing 1 can be welded to each other satisfactorily with a uniform depth over the entire circumference. In the case, when the laser beam of the high output is made one round, it is of course that it is made one round either at a uniform or definite high output or by reducing a high output stepwise at the plural number of stages. According to the present embodiment, the open air is sucked into the cylindrical shield 70' through the air-intake openings 23, 23, ... by the above-mentioned suction evacuation action and always exhausted to the outside through the cylindrical shield 70' while carrying the fume generated in the laser welding, so that the protection glass 5 can prevent the fumes from adhering thereto

FIG. 10

~~etermined  
so there  
heated~~

0 1 2 3 4 5 6 7 8 9 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48 49 50 51 52 53 54 55 56 57 58 59 60 61 62 63 64 65 66 67 68 69 70 71 72 73 74 75 76 77 78 79 80 81 82 83 84 85 86 87 88 89 90 91 92 93 94 95 96 97 98 99

Furthermore, if the projection 2a is made a solid columnar projection, the columnar projection is clamped by an alligator clip at a charging step after completion of the laser welding, and even if a spark is generated between the projection and the

In addition, in a case where the focused point of the laser beam is so positioned as to hit on such an outer peripheral edge of the pole 2 that is inside the annular abutting portions, and the laser beam is applied along the inner peripheral edge, it is advantageous because the thermal influence exerted to the resin of the lid around the lead bushing 1 can be further reduced.

Thus, the present invention is applicable to the production of various lead-acid batteries such as a lead-acid battery for an electric automobile, a lead-acid battery for an automobile, an installed lead-acid battery and the like.